

# *WindRiver Fence*

*Making safe HDPE horse fence since 1991*

*Property: ASTM for HDPE Typical Values*

*Density (Lbs./Cu. In.).....D6111.....0.0023 – 0.0028*

*Compression (psi@0.4").....D6108.....3000 – 3100*

*Tensile (psi).....D638.....2100 – 2600*

*Flexural Strength (psi).....D6109.....2000 – 3000*

*Tangent Modulus.....216,000 – 222,000*

*Coefficient of Thermal Expansion ..D696......00007*

*Vicat Softening Point (F).....150 – 160 (F)*

*Brittleness Point (F).....(-100) – (-104) (F)*